



E.P.O. / 5657



26.05.04




INVESTOR IN PEOPLE

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ




I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Stephen Hordley

Dated

5 March 2004

BEST AVAILABLE COPY

Patents Act 1977
(Rule 16)

THE PATENT OFFICE
RN
26 JUN 2003

The
Patent
Office

26 JUN 03 E81385 P 0314833.5
P01/700 000-0314833.5
1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office
Cardiff Road
Newport
Gwent NP9 1RH

1.	Your reference	GB Case	PI3-22348/P2
2.	Patent application number (The Patent Office will fill in this part)	26 JUN 2003	0314833.5
3.	Full name, address and postcode of the or of each applicant (underline all surnames)	Ciba Specialty Chemicals Water Treatments Limited Cleckheaton Road Low Moor Bradford West Yorkshire BD12 0JZ	
	Patent ADP number (if you know it)	07585391005	
	If the applicant is a corporate body, give the country/state of its incorporation	England	
4.	Title of invention	POLYMERIC SURFACTANT	
5.	Name of your agent (if you have one)	Ciba Specialty Chemicals Water Treatments Limited	
	"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	Patents Department PO Box 38 Cleckheaton Road Low Moor Bradford West Yorkshire BD12 0JZ	
	Patents ADP number (if you know it)	07585391002 ✓	
6.	If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)
			Date of filing (day/month/year)
7.	If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day/month/year)
8.	Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if: a) any applicant named in part 2 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. (see note (ii))	YES	

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form •

Description 17 ✓

Claim(s) 4 ✓

Abstract 1 ✓ *21*

Drawing(s) •

10. If you are also filing any of the following, state how many against each item.

Priority documents •

Translations of priority documents •

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*) •Request for preliminary examination and search (*Patents Form 9/77*) 1 ✓Request for substantive examination (*Patents Form 10/77*) •

Any other documents (please specify) •

11. I/We request the grant of a patent on the basis of this application

Signature

Date

JAS

26 June 2003

12. Name and daytime telephone number of person to contact in the United Kingdom Jane Spinks 01274 417558

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

DUPLICATE

Polymeric Surfactant

The present invention concerns novel polymeric surfactants and methods of making them. These polymeric surfactants are particularly suitable for making emulsions and dispersions.

Polymeric surfactants are frequently used for interacting with the interface in a variety of multiphase systems. By multiphase systems, we include systems that contain two or more phases, such as emulsions and dispersions. In the preparation and/or stabilisation of emulsions and dispersions, it is common practice to employ a polymeric surfactant in order to stabilise the interface between the continuous and discontinuous phases. Typically polymeric surfactants comprise a portion of the polymer molecule which has an affinity for one phase and a portion which has an affinity for the other phase. Such a polymeric surfactant may be a block copolymer containing a block of hydrophobic repeating monomer units and a block of hydrophilic repeating monomer units. The polymeric surfactants can be graft polymers containing a main polymeric or oligomeric backbone, having an affinity for one phase, and pendant polymeric or oligomeric chains, having an affinity for another phase.

GB-A-2002400 reveals surfactants which are blends of oil soluble copolymers with conventional surfactants for use in the emulsification of water in hydrocarbon fuel oils. The polymers can be block polymers or graft polymers and comprise at least two polymeric components derived from an oil soluble complex monocarboxylic acid, obtained by interesterification of one or more mono hydroxy-monocarboxylic acids together with a hydroxyl free monocarboxylic acid acting as a chain terminator and a polymeric component derived from a water soluble polyalkylene glycol.

GB-A-2116205 describes polymeric surfactants for the emulsification of methanol or ethanol in hydrocarbon liquids, such as diesel oil. The surfactant

comprises a blend of a first element which is either a block polymer or a graft polymer which is the residue of an oil soluble complex monocarboxylic acid and another polymeric component which is the residue of a water-soluble polyalkylene glycol or polyalkylene oxy polyol and a second element which is a

- 5 conventional non-ionic, non polymeric surfactant. The block or graft polymers can be prepared in the same manner as described in GB-A-2002400.

- WO-A-01/60901 discloses low foaming surfactants which are water-soluble or water dispersible branched polymeric compounds. The branched compounds are the based catalysed reaction products of a first component which is a C 3 to 10 alkane trihalide or a C 3 to 10 halo alkane substituted by two epoxy oxygen atoms each of which are attached to two adjacent carbon atoms of the halo alkane and a second component which is an organic group of up to 36 carbon atoms carrying hydroxy, amino or thiol groups. The hydroxy, amino or thiol groups can be separated from the organic group by an alkoxy group and which contains up to 200 repeating units.

- EP-A- 357149 concerns stable emulsion formulations of water insoluble organic pesticides, prepared by mixing the pesticide with an aqueous dispersions of a graft copolymer surfactant. This polymeric surfactant comprises a reactive polymeric surfactant base polymer and a nonionic hydrophobic grafted composition. The polymer comprises a hydrophilic backbone with pendant grafted hydrophobic groups. It is stated that the surfactants may be obtained by a combination of pH independent anionic monomers, such as sulphonate monomers, and nonionic monomers contentions hydrophobic and hydrophilic units. The reactive polymeric surfactant contains grafting sites which are typically vinyl groups linked to the backbone through and ester, amide or quaternary ammonium connection. Side chains are bonded to the reactive surfactant at the grafting sites. The side-chain is a copolymer formed from ethylenically unsaturated monomers, for example styrene, acrylates or meth acrylates etc. Thus the graft polymer is formed from a base polymer which

carries ethylenically unsaturated functionalities that can be polymerised with a hydrophilic monomers or groups which will copolymerise with the hydrophobic monomers.

- 5 EP-A-198307 relates to a coating composition comprising a graft copolymer having surfactant properties. The copolymer is the reaction product of an anhydride copolymer with a vinyl copolymer comprising vinyl chloride, carboxylic ester, and a source of hydroxyl groups. The anhydride copolymer comprises the reaction product of an aromatic monomer and a dicarboxylic acid
- 10 anhydride.

- EP-A-268705 describes a polymeric surfactant which is a block copolymer comprising chemically linked polymeric blocks. The first block part of the polymer consists of homo- or copolymerised non polar monomeric ethylenically
- 15 unsaturated compounds and a second block consists of ethylenically unsaturated monomer containing an epoxy group that has been transformed into an ionic group.

- Graft polymeric surfactants described in the aforementioned references are all
- 20 prepared by processes involving either the formation of a base polymer which carries ethylenically unsaturated groups onto which ethylenically unsaturated monomers are grafted or the formation of a base polymer which carries a functional group onto which molecules can be grafted.

- 25 Graft polymers are particularly suitable as polymeric surfactants since they will typically contain a backbone which will preferentially associate with one phase and grafted moieties which preferentially associate with a different phase.

- However, graft polymers suitable as surfactants are generally difficult to make
- 30 and often involved a first macro monomer which has a reactive end group which is then subjected to a second polymerisation process. This is difficult to achieve

in good yields and tends to be restricted to short chain molecules and/or low concentrations because of viscosity limitations. Alternatively, graft polymers can be prepared by reacting molecules, for instance polymer chains, containing a reactive end group that reacts with reactive groups and a base polymer

5 substrate. However, the preparation of the base polymer and molecules containing said reactive groups and then reacting these two preformed entities together is complex and can be difficult to prepare in a sufficiently high yield. A further difficulty is that the process can be difficult to control can lead to problems with product quality.

10

The preparation of graft polymers in general is well-documented in the prior art. Numerous methods are given in the literature for preparing a multitude of different types of graft polymers, covering a variety of different chemical structures and physical forms. Typically graft polymers described in the literature are used for a variety of applications. In general the preparation of a specific graft polymer, having particular properties designed for a particular application, is dependent upon the choice of starting materials and the process conditions.

20 An example of the preparation of graft polymers includes GB 922457, which reveals a process for making graft copolymers by dissolving a polyalkylene glycol in at least one monomer, such as vinyl esters and esters of acrylic or methacrylic acid, either in the presence or the absence of a solvent. The process employs a free radical polymerisation catalyst under the action of actinic light. Dibenzoyl peroxide is proposed as an initiator, which can decompose thermally or by ultraviolet light. This process would involve a type I photo initiation.

US 4846994 and US 4846995 each propose the use of graft polymers prepared according to GB 922457 as greyness inhibitors in the wash and after treatment

30

of textiles. US 5635554 describes low viscosity formulations containing graft polymers made in the same way for use as viscosity reducing additives.

An article entitled, "Ultraviolet cured pressure sensitive adhesives", Kenneth C
5 Stueben, Union Carbide Corporation, Polymer Science and Technology, 1984
(29) 319-350, describes photo cure of mono- and multifunctional acrylate-poly
ethers-benzophenone blends. Grafting is effected by ultraviolet radiation. The
reference suggests that carbamoyloxy alkyl acrylates can be grafted onto
polyethylene oxides of molecular weight 1700 to 90,000 preferably 2500 to
10 21,000. The graft polymer thus formed would tend to have a high molecular
weight in order to function as a pressure sensitive adhesive.

GB 1439132 discloses a method for the production of a hydrophilic grafted
polymer product. Gamma radiation is used to generate radicals along a
15 hydrophobic polymer backbone from which hydrophilic monomer will
polymerise. The process does not use a chemical polymerisation initiator.

GB 1032605 also reveals preparing graft copolymers using high energy
radiation or by chemical free radical generating catalysts.

20

An objective of the present invention is to provide a polymeric surfactant by an
alternative and more convenient route. It is also an objective to provide a range
of polymeric surfactants which are particularly suitable for stabilising water in oil
emulsions, oil in water emulsions, dispersions of solids in an aqueous medium
25 and dispersions of solids in a oil based medium.

According to one aspect of the invention we provide a polymeric surfactant
formed by the reaction of an oligomeric or polymeric substrate with at least one
ethylenically unsaturated monomer, wherein the reaction is conducted in the
30 presence of a type II photo initiator and by the action of actinic radiation.

The action of the actinic radiation upon the photo initiator induces photo-initiation. In principle there are two types of photoinitiation mechanisms according to the process by which the initiating radicals are formed. Compounds undergoing homolytic cleavage are termed type I photoinitiators, which is not
5 the case in the present invention, and compounds that interact with a second molecule (known as co-initiators) as in the present invention, are known as type II photo initiators. The reaction pathways available for Type II photoinitiators are via hydrogen abstraction or electron transfer (followed by proton transfer) mechanisms, but under certain conditions both mechanisms may be involved.
10

These type II photoinitiations thus require co-initiators (usually hydrogen donating compounds typified by amines, alcohols, thiols or ethers) generating the radicals that trigger polymerisation and thus this type of initiation has the potential to incorporate hydrogen donating compounds into polymers (i.e.
15 photografted polymers). However, photo initiated graft polymerisation using type II initiators has previously only been used to prepare hard resinous solids or adhesives.

Generally in the preparation of graft polymeric surfactants it can be difficult to
20 control the molecular weight, in particular the molecular weight of the pendant graft polymer chains. Furthermore, the overall structure of the graft polymer is critical in order to provide the right balance of lipophilic and hydrophilic characteristics. Surprisingly, we have been able to provide a graft polymer, which is suitable as a surfactant, using a photo initiated graft polymerisation
25 process employing type II photo initiators. Thus the process not only has the advantage in terms of convenience, but also can be controlled easily to provide a surfactant with the right properties for a given application. Hence the present invention conveniently provides a range of surfactants suitable for a variety of multiphase systems. The surfactants of the present invention have a unique
30 molecular structure and in particular comprise polymer chains, formed from the

chosen monomer, grafted directly onto the substrate by covalent bonding at a position on the substrate previously occupied by hydrogen atoms.

5 The multiphase systems which can be stabilised by the surfactants of the present invention include combinations of various immiscible liquids, for instance as emulsions or dispersions of particulate solids in a variety of liquids. Therefore, the surfactant will possess moieties which will associate with each of the liquid phases in liquid liquid systems or moieties which associate with the liquid phase and the surface of the solid-phase in dispersions of solids. Such
10 liquid liquid systems include emulsions of organic polar liquids in non polar hydrocarbons. Preferably the liquid liquid systems include one phase which is aqueous, for instance water in oil emulsions or oil in water emulsions. Therefore a preferred polymeric surfactant will contain hydrophilic portions which associate with the aqueous phase and hydrophobic and/or lipophilic
15 portions which associate with an oil phase. Preferably the polymeric surfactant is an amphiphilic polymer.

The polymeric surfactants according to the invention may be used in any of the typical applications of surfactants. When the surfactants are used to stabilise
20 the interface between phases of multiphase compositions, the polymeric surfactant is desirably soluble or at least dispersible in one or more of the phases. In one preferred system the polymeric surfactant is water-soluble. In another preferred system the polymeric surfactant is oil soluble.

25 It is important that the polymeric surfactant has a molecular structure and size, which enables it to partition into a liquid phase and to be able to form micelles and/or associate with the interface of another phase. If the molecular weight is too high, the polymer will not readily function as a surfactant. Typically the molecular weight should be below 100,000, preferably below 50,000. Usually
30 the surfactant has a molecular weight in excess of 1,000, for instance in the

range of 2,000 or 3,000 to 50,000. More preferred molecular weights are from 6,000 for 25,000, especially 10,000 to 20,000.

- The polymeric surfactant should be prepared from a substrate, to which grafting of ethylenically unsaturated monomers is enabled using a type II photo initiator. In this process a substrate may be regarded as a co initiator for the type II photo initiator. Therefore, although separate co initiators are not precluded, and for some systems may be beneficial, inclusion of a co initiator additional to the substrate is not essential. Typically, the substrate can be any natural polymer, sugars, vinyl addition polymers, polyethers, synthetic or semisynthetic condensation polymers, or inorganic substances and in which the substrate contains one or more abstractable hydrogen atoms. Examples of preferred substrates include substances selected from the group consisting of polyalkylene oxides, polyalkylene glycols, (meth) acrylamide polymers, (meth) acrylic acid polymers (esters or salts thereof), polyvinyl alcohol, polyvinyl acetate, polyvinylpyrrolidone, polyethylenimine, polyesters, polyamides, sugars, polysaccharides, amino acids, proteins and inorganic substances containing abstractable hydrogen.
- The at least one ethylenically unsaturated monomer which is grafted onto the substrate can be any monomer which readily undergoes direct reaction with the activated sites on the substrate. The activated sites on the substrate would be at a position where the type II photo initiator has generated a radical. The monomer molecule will react through the double bond and become covalently bonded directly to the substrate. The monomer unit would carry a radical onto which a further monomer molecule will react through the double bond and this process will continue to form a grafted polymer chain. Of course further polymer chains could be formed off these formed polymer chains by a similar process resulting in secondary grafting. Suitably the monomer comprises any one of acrylic, vinylic and allylic monomers.

The choice of monomer will normally depend upon the properties required for the polymeric surfactant. Therefore, an oil soluble surfactant which stabilises an aqueous dispersed phase in an oil may be prepared by grafting hydrophobic monomers onto a water soluble substrate. For the reverse system, a water-soluble surfactant which stabilises an oil phase in water can be made by grafting hydrophilic monomers on to a hydrophobic substrate. Examples of suitable monomers for use in the present invention include any in the group consisting of (meth) acrylamides, N-vinyl pyrrolidinone, hydroxy ethyl acrylate, (meth) acrylic acid or salts thereof, maleic acid or salts thereof, itaconic acid or salts thereof, 2-acrylamido-2-methyl propane sulfonic acid or salts thereof, vinyl sulfonic acid, allyl sulfonic acid, dialkyl amino alkyl (meth) acrylates or quaternary ammonium or acid addition salts thereof, dialkyl amino alkyl (meth) acrylamides or quaternary ammonium or acid addition salts thereof, diallyl dialkyl ammonium halide, styrenes, C1-30 alkyl (meth) acrylates and (meth) acrylonitrile.

The weight ratio of substrate to grafted moiety (i.e. portion formed from the ethylenically unsaturated monomer) is desirably in the range of 99:1 to 1:99. Preferably the ratio would be in the range 50:1 – 1:50.

20

The type II photo initiator may be any substance which is capable of a photoreaction with a so-called co initiator or substrate to form a radical when exposed to a suitable actinic radiation. Preferably, the photo initiator may be any one of benzophenone, diaryl ketones, xanthenes, thioxanthenes, acridones, anthraquinones, diketones, ketocoumarines or imides. If the photoreaction is performed in water or a polar solvent, the use of water-soluble type II photoinitiators, such as the salts of ammoniumalkyl or sulfonylalkyl derivatives of benzophenones or thioxanthenes, may be preferable. It is further possible to use type II photoinitiators substituted by co-polymerisable groups that are co-polymerised with the growing side chain, or type II photoinitiators that are bound to a polymer backbone. It is in addition possible to use blends of one or more of

30

the previously mentioned type II photoinitiators. The choice of actinic radiation will depend upon the particular initiator used and will also depend to some extent on the reactants and if used the solvent. Desirably the actinic radiation includes electromagnetic radiation and preferably will be ultraviolet light, infrared light, or visible light.

According to a further aspect of the invention we provide a method of producing a polymeric surfactant comprising contacting an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer and a type II photo initiator to form a reaction mixture and wherein the reaction mixture is subjected to actinic radiation to induce grafting of monomer onto the substrate and photo polymerisation to form a polymeric surfactant.

Preferably, the method employs any of the aforementioned features relating to the polymeric surfactant.

The ratio of substrate to ethylenically unsaturated monomer will be appropriate to provide the desired ratio of substrate component to grafted polymer chains as described above.

The amount of type II photo initiator will depend upon many factors, including choice of photo initiator, substrate, monomer and solvent (if used). Typically the photo initiator may be used in amount of 0.005 – 30% w/w upon substrate.

It is particularly preferable to use ultraviolet light as the actinic radiation. The UV light source may include low, medium or high-pressure UV lamps, metal halide lamps, microwave-stimulated metal vapor lamps, carbon arc lamps, xenon arc lamps, excimer lamps, superactinic fluorescent tubes, fluorescent lamps or light emitting diodes, and the UV spectral output should ideally match the UV absorbance of the chosen photoinitiator.

- A suitable UV light source for a typical photoinitiator such as benzophenone can be a medium pressure mercury UV lamp. Desirably, the UV light should have a wavelength in the range of 200 – 500 nm and a peak power density of at least 0.1 mW/cm² and normally at least 0.5 mW/cm². Usually the peak power
- 5 density will be in the range of 1 mW/cm² to 200W/cm², and typically 1.5 mW/cm² to 100 mW/cm². The exposure length of the UV irradiation can be as short as a fraction of a second to several hours. Typically, the irradiation will be for a duration of 1 – 300 minutes.
- 10 The UV light source can be applied to the reactants internally or externally provided there is no barrier to the specific wavelength of UV light that is required by the photoinitiator to function.
- The reactant mixture can be introduced into the reactor vessel separately,
- 15 together as a mixture, or passed through an irradiating chamber in a continuous fashion, or can be recycled with similar or different monomer/initiators mixtures.
- The reactants can be degassed in order to remove unwanted oxygen from the reaction medium. Degassing is typically carried out by passing an inert gas
- 20 such as nitrogen to the liquid reaction medium for sufficient time and after sufficient rate to remove dissolved and entrained oxygen or by using a vacuum technique (3 or 4 freeze-pump thaw cycles) at $<10^{-4}$ Torr.
- The photopolymerisation reaction can be carried out in a range of suitable
- 25 solvents. Preferably, the solvents should not participate as hydrogen donors in the photo initiation step. The solvents which can be used for this purpose include amongst others methanol, toluene, cyclohexane, acetonitrile, dimethylformamide and water etc.
- 30 Therefore in one preferred form of the method of preparing the polymeric surfactant, the substrate, ethylenically unsaturated monomer and type II photo

Initiator are combined together in a suitable solvent to form a reaction mixture. All of the components may be dissolved in the solvent or one or more of the components may be dispersed throughout the solvent, provided that this does not adversely affect the reaction. The reaction mixture is then irradiated using
5 UV light to initiate the reaction. The solvent used can be present in an amount of 10 - 90% of the reaction mixture.

The photopolymerisation reaction can be carried out at a range of different temperatures, isothermally or adiabatically. Typical temperature ranges include
10 10 - 100 °C.

The polymeric surfactant of the present invention, which can be obtained by the aforementioned method, is particularly suitable for stabilising an interface between phases in an emulsion or a dispersion.

15

Thus according to a still further aspect of the present invention we provide a composition comprising a discontinuous phase distributed throughout a continuous phase comprising an interface between phases and in which a polymeric surfactant is located at the interface,
20 in which the polymeric surfactant is formed by the reaction of an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer, wherein the reaction is conducted in the presence of a type II photo initiator and by the action of actinic radiation.

25 Preferably, the method employs any of the aforementioned preferred features relating to the polymeric surfactant.

This aspect of the present invention is applicable to any multiphase system typically stabilised by surfactants. Generally, the composition can be water-
30 based or oil based. By an oil based system we mean that the continuous phase comprises a hydrocarbon or other water immiscible or hydrophobic liquid.

Typically in such an oil based system the discontinuous phase will comprise a substance which is insoluble in and immiscible with the continuous phase. This may for instance be a polar organic liquid, such as ethanol or methanol. However, preferably the discontinuous phase is aqueous.

5

In another form, the composition can be water-based and in which case the continuous phase is aqueous. In the same way as in the oil based system, the discontinuous phase should comprise a substance which is insoluble in and immiscible with the continuous phase. Preferably, the discontinuous phase comprises a hydrocarbon or a water immiscible liquid.

10

In the case of either an oil based composition or a water-based composition it is preferred that the polymeric surfactant is dissolved in the continuous phase. Thus in a preferred system, the polymeric surfactant is located at the interface between phases but preferentially partitions into the continuous phase. In one particularly preferred composition two polymeric surfactants according to the invention are employed, one of which is preferentially dissolved in the continuous phase and a second polymeric surfactant is preferentially dissolved in the discontinuous phase. Such a system includes doubly stabilised emulsions that are highly stable.

15

20

The invention includes systems in which the continuous phase acts as a carrier for ingredients held in the discontinuous phase. For instance the composition may comprise an emulsion in which the discontinuous phase comprises at least one ethylenically unsaturated monomer. The continuous phase may be either an oil or aqueous liquid depending upon the monomer. Thus such a system is useful for emulsion polymerisation and the formation of emulsions or dispersions comprising in the discontinuous phase a polymer formed from at least one ethylenically unsaturated monomer.

25

30

Other emulsions or dispersions according to the invention include aqueous emulsions of agriculturally active substances such as herbicides or pesticides.

~~The composition may for instance be an aqueous emulsion paint.~~ In one
5 preferred form the composition is an aqueous alkyd resin paint formulation in which the continuous phase is aqueous and the discontinuous phase comprises the alkyd resin.

Alternatively, the composition may be for instance an oil in water in oil emulsion
10 or a water in oil in water emulsion.

The discontinuous phase of the composition may be particulate solid. Typically, the particulate solid is selected from the group consisting of calcium carbonate, titanium dioxide, kaolinite, swellable clays, barium sulphate and pigments. Thus
15 the composition may be any of the group consisting of filler dispersions, microparticulate retention aid dispersions, drilling muds and pigment dispersions.

In the case where the composition is an emulsion method comprises dissolving
20 or dispersing the polymeric surfactant into a first liquid and mixing a second liquid, which is immiscible with the first liquid and then forming the emulsion. Analogously, but the composition is a dispersion of a particulate solid, it may be prepared by dissolving the polymeric surfactant into a liquid continuous phase and mixing a particulate solid into the liquid continuous phase and then
25 forming the dispersion.

The following examples are illustrations of the invention.

15

Example 1

Preparation of 7:3 w/w PEG 2000:MA graft polymer using Benzophenone, and its emulsification properties.

- 5 6.1 g Methyl acrylate (MA) and 14.0 g PEG 2000 were added to a jar. Methanol (16.9 g) was added to jar pipette wise until all PEG 2000 dissolved. 0.25 g Benzophenone was added to the PEG/MA and the sample mixed until homogenous.
- 10 The homogenous sample (2.0 g) was weighed into 10mL borosilicate glass tube. The sample was placed under a medium pressure Hg Black Ray UV lamp 360-370 nm, 40mW/cm². After 15 min the sample was rotated through 180° to ensure complete irradiation of the whole sample to form a polymerised product.
- 15 GC analysis of the sample, pre-radiation and after 30 min of UV exposure, was performed. It was found that all of the MA had reacted (>99.5%) and therefore irradiation was discontinued .

- After UV irradiation the sample of polymerised product was still mobile Methanol
- 20 was removed prior to the polymer being tested for emulsification properties.

- The polymerised product sample (1.5 g) was put into rotary floris, and dried on the rotary evaporator, 50 °C, 100 mbar vac until at constant weight. 1.1 g of dry polymer was obtained which was dissolved in 9.0 g toluene (about 10 wt/wt%).
- 25 4.5 g of polymer/toluene solution was transferred to a sealed tube and 5 g of de-ionised water added. The sample was shaken and left to stand for 5 weeks.

30

Emulsification results

A good white emulsion of the toluene and water was formed prior to mixing. After shaking, the emulsion clung to the glass well indicating an oil in water

- 5 emulsion, which was found to be stable over a period of time.

Example 2

Preparation of 1:1:5.4 w/w/w Poly(DMAEA):butylacrylate:acrylamide graft
copolymer (Polymer A) using benzophenone and use as a pigment dispersant
10 (all parts by weight).

- Dimethylaminoethylacrylate (DMAEA) (23 parts), n-butylacrylate (24 parts), methanol (37 parts) and benzophenone (1 part) were added a borosilicate glass tube, capped and shaken until the mixture was fully homogeneous. The tube
15 was next placed almost horizontally under a medium pressure Hg Black Ray UV lamp rotated slowly and irradiated at 360-370 nm, 40mW/cm² for 12 minutes. Analysis of the product after this time by gas chromatography indicated that >95% of the DMAEA and n-butylacrylate had been consumed. The sample was allowed to rotate under the UV light for a further 60 minutes to allow any
20 residual monomers to react.

- Part of this product mixture (7.5 parts) was transferred to a second borosilicate tube containing benzophenone (1 part), acrylamide (13 parts) and methanol (46 parts). After capping, the mixture was shaken until it became homogeneous.
25 This reaction mixture was then subjected to UV irradiation. After a few minutes a white precipitate formed and the sample was irradiated with the UV light for a total of 30 minutes to ensure that all the monomers had been fully reacted. The solvent was removed by heating to 70 degrees C for 15 minutes to afford the graft copolymer as a hard clear film (Polymer A).

Evaluation of Polymer A as a Pigment Dispersant

Polymer A (0.5 parts) was added to an aqueous suspension (100 parts of 5% w/w) of Pigment Blue 60 (available from Ciba Specialty Chemicals Ltd), mixed well by hand, and dried at 80 °C for 1 hour. The solid recovered was added to water (50 mg per 200mL) and gently stirred for 10 minutes. A stable dispersion of the pigment was formed showing good colour density. As a control the equivalent aqueous suspension of Pigment Blue 60 in the absence of Polymer A did not form a stable dispersion and the pigment started to settle to form a sediment.

Claims

1. A polymeric surfactant formed by the reaction of an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer, wherein the reaction is conducted in the presence of a type II photo-initiator and
- 5 by the action of actinic radiation.
2. A polymeric surfactant according to claim 1, which is an amphiphilic polymer.
3. A polymeric surfactant according to claim 1 or claim 2, which is water-soluble.
- 10 4. A polymeric surfactant according to any of claims 1 to 3, which is oil soluble.
5. A polymeric surfactant according to any of claims 1 to 4, which has a molecular weight below 100,000, preferably below 50,000.
- 15 6. A polymeric surfactant according to any of claims 1 to 5, in which the substrate is selected from the group consisting of polyalkylene oxides, polyalkylene glycols, (meth) acrylamide polymers, (meth) acrylic acid polymers (esters or salts thereof), polyvinyl alcohol, polyvinyl acetate, polyvinylpyrrolidone, polyethylenimine, polyesters, polyamides, sugars, polysaccharides, amino acids, proteins and inorganic substances containing
- 20 abstractable hydrogen.
7. A polymeric surfactant according to any of claims 1 to 6, in which the monomer comprises any one of acrylic, vinylic and allylic monomers.
8. A polymeric surfactant according to any of claims 1 to 7, in which the monomer comprises any of the group consisting of (meth) acrylamides, N-vinyl
- 25 pyrrolidone, hydroxy ethyl acrylate, (meth) acrylic acid or salts thereof, maleic acid or salts thereof, itaconic acid or salts thereof, 2-acrylamido-2-methyl propane sulfonic acid or salts thereof, vinyl sulfonic acid, allyl sulfonic acid, dialkyl amino alkyl (meth) acrylates or quaternary ammonium or acid addition salts thereof, dialkyl amino alkyl (meth) acrylamides or quaternary ammonium or
- 30 acid addition salts thereof, diallyl dialkyl ammonium halide, styrenes, C1-30 alkyl (meth) acrylates and (meth) acrylonitrile.

9. A polymeric surfactant according to any of claims 1 to 8, in which the photoinitiator comprises one or more compounds selected from the group consisting of benzophenone, diaryl ketones, xanthenes, thioxanthenes, acridones, anthraquinones, diketones, 2-ketocoumarins, and imides.
- 5 10. A polymeric surfactant according to any of claims 1 to 9, in which the actinic radiation is selected from ultraviolet light, infrared light, and visible light.
11. A method of producing a polymeric surfactant comprising contacting an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer and a type II photo initiator to form a reaction mixture and wherein the
- 10 reaction mixture is subject to actinic radiation to induce grafting of monomer onto the substrate and photo polymerisation to form a polymeric surfactant.
12. A method according to claim 11 in which the reaction mixture is dissolved or dispersed in a liquid medium.
13. A method according to claim 12 in which the liquid medium is selected
- 15 from the group consisting of methanol, toluene, cyclohexane, acetonitrile, dimethylformamide and water.
14. A method according to any of claims 11 to 13 including the features of any of claims 2 to 10.
15. Use of a polymeric surfactant defined by any of claims 1 to 10 or
- 20 obtainable by any of claims 11 to 14 for the purpose of stabilising an interface between phases in an emulsion or a dispersion.
16. A composition comprising a discontinuous phase distributed throughout a continuous phase comprising is an interface between phases and in which a polymeric surfactant is located at the interface,
- 25 in which the polymeric surfactant is formed by the reaction of an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer, wherein the reaction is conducted in the presence of a type II photo initiator and by the action of actinic radiation.
17. A composition according to claim 16 in which the polymeric surfactant is
- 30 defined by any of claims 2 to 10 or obtainable by the method of any of claims 11 to 14.

18. A composition according to claim 16 or claim 17 in which the continuous phase comprises a hydrocarbon or a water immiscible liquid.
19. A composition according to any of claims 16 to 18 in which the discontinuous phase is aqueous.
-
- 5 20. A composition according to claim 16 or claim 17 in which the continuous phase is aqueous.
21. A composition according to claim 16, claim 17 or claim 20 in which the discontinuous phase comprises a hydrocarbon or a water immiscible liquid.
22. A composition according to any of claims 16 to 21 in which the polymeric
- 10 surfactant is preferentially dissolved in the continuous phase.
23. A composition according to any of claims 16 to 22 comprising a first polymeric surfactant and a second polymeric surfactant in which the first polymeric surfactant is preferentially dissolved in the continuous phase and a
- 15 second polymeric surfactant is preferentially dissolved in the discontinuous phase.
24. A composition according to any of claims 16 to 23 in which the discontinuous phase comprises at least one ethylenically unsaturated monomer or a polymer formed from at least one ethylenically unsaturated monomer.
25. A composition according to any of claims 16 to 23 which is an aqueous
- 20 emulsion paint.
26. A composition according to claim 25 in which the aqueous emulsion paint is an aqueous alkyd resin paint formulation in which the continuous phase is aqueous and the discontinuous phase comprises the alkyd resin.
27. A composition according to any of claims 16 to 26, which is an oil in
- 25 water in oil emulsion.
28. A composition according to any of claims 16 to 26, which is a water in oil in water emulsion.
29. A composition according to any of claims 16 to 28 in which the discontinuous phase comprises a particulate solid.

30. A composition according to claim 29 in which the particulate solid is selected from the group consisting of calcium carbonate, titanium dioxide, kaolinite, swellable clays, barium sulphate and pigments.

5 31. A composition according to claim 29 or claim 30 which is selected from the group consisting of filler dispersions, microparticulate retention aid dispersions, drilling muds and pigment dispersions.

32. A method of making a composition according to any of claims 16 to 28, wherein composition is an emulsion, comprising dissolving or dispersing the polymeric surfactant, as defined by claims 1 to 10 or obtainable by the methods
10 of claims 11 to 14, into a first liquid and mixing a second liquid, which is immiscible with the first liquid and then forming the emulsion.

33. A method of making a composition according to any of claims 16 to 31, wherein the composition is a dispersion, comprising dissolving or dispersing the polymeric surfactant, as defined by claims 1 to 10 or obtainable by the methods
15 of claims 11 to 14, into a liquid continuous phase and mixing a particulate solid into the liquid continuous phase and then forming the dispersion.

22

Abstract

Polymeric Surfactant

- 5 A polymeric surfactant formed by the reaction of an oligomeric or polymeric substrate with at least one ethylenically unsaturated monomer, wherein the reaction is conducted in the presence of a type II photo initiator and by the action of actinic radiation. The polymeric surfactant is useful for stabilising the interface in emulsions or dispersions.

10

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.